

## AR AG AF Coating Performance Test Report

Testing equipment: spectrophotometer, haze meter, friction tester

### 1. AR Coating Test Data

Visible light transmittance  $\geq 96\%$ , surface reflectance  $\leq 2\%$ , no rainbow distortion

### 2. AF Coating Test Data

Water contact angle  $\geq 110^\circ$ , withstand 1000 times alcohol wiping without coating peeling

### 3. AG Coating Test Data

Custom haze 5%-30%, uniform matte surface, no bright spot, clear display imaging

### 4. Composite Coating Test Result

AR+AF / AG+AF maintain both optical performance and stain resistance

### 5. Test Conclusion

Batch products pass full optical and wear resistance test, all test records available for customer audit.